


# BS EN ISO 11925-2: 2010



## Ignitability Of Building Products Subjected To Direct Impingement Of Flame Part 2: Single Flame Source Test

A Report To: Kingspan Insulation Ltd

Document Reference: 358292

Date: 9<sup>th</sup> November 2015

Issue No.: 1

Page 1

**Testing  
Advising  
Assuring**

## Executive Summary

**Objective** To determine the performance of the following product when tested in accordance with BS EN ISO 11925-2:2010.


Generic Description	Product reference	Thickness	Weight per unit area or density
Black foil faced thermoset phenolic insulation board (silver foil on reverse)	"Kooltherm K15"	50mm	Confidential
<b>Individual components used to manufacture composite:</b>			
Aluminium foil black in colour (test face)	Confidential	Confidential	Confidential
Foam	"K15"	50mm	Confidential
Aluminium foil	Confidential	Confidential	Confidential
Substrate	"Promat Brandschutzbauplatten; Promatect-H"	12mm	870kg/m <sup>3</sup>
<b>Please see page 5 of this test report for the full description of the product tested</b>			

**Test Sponsor** Kingspan Insulation Limited, Pembridge, Leominster, Herefordshire, HR6 9LA

**Test Results:** On each set of six specimens which were tested, the flame tip did not reach a distance of 150mm before the end of the test.


**Date of Test** 28<sup>th</sup> October 2015

## Signatories


---

Responsible Officer  
K. Hughes \*  
Technical Officer


---

Authorised  
S. Deeming\*  
Business Unit Head

\* For and on behalf of **Exova Warringtonfire**.

Report Issued: 9<sup>th</sup> November 2015

This version of the report has been produced from a .pdf format electronic file that has been provided by **Exova Warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of **Exova Warringtonfire**.

Document No.: 358292

Page No.: 2 of 8

Author: K Hughes

Issue Date: 9<sup>th</sup> November 2015

Client: Kingspan Insulation Ltd

Issue No.: 1



CONTENTS

PAGE NO.

**EXECUTIVE SUMMARY ..... 2**

**SIGNATORIES ..... 2**

**TEST DETAILS ..... 4**

**DESCRIPTION OF TEST SPECIMENS ..... 5**

**TEST RESULTS..... 6**

**TABLE 1..... 7**

**TABLE 2..... 7**

**TABLE 3..... 7**

**REVISION HISTORY..... 8**



## Test Details

<b>Purpose of test</b>	<p>To determine the performance of specimens of a product when they are subjected to the conditions of the test specified in BS EN ISO 11925-2:2010 "Reaction to Fire tests - Ignitability Of Building Products Subjected to Direct Impingement of Flame – Part 2: Single Flame Source Test".</p> <p>The test was performed in accordance with the procedure specified in BS EN ISO 11925-2:2010 Reaction to Fire Tests - Ignitability of Building Products subjected to direct impingement of flame – Part 2: Single Flame Source Test, and this report should be read in conjunction with that BS EN ISO Standard.</p>
<b>Scope of test</b>	BS EN ISO 11925-2 specifies a method of test for determining the ignitability of building products by direct small flame impingement under zero impressed irradiance using specimens tested in a vertical orientation.
<b>Fire test study group/EGOLF</b>	Certain aspects of some fire test specifications are open to different interpretations. The Fire Test Study Group and EGOLF have identified a number of such areas and have agreed Resolutions which define common agreement of interpretations between fire test laboratories which are members of the Groups. Where such Resolutions are applicable to this test they have been followed.
<b>Instruction to test</b>	The test was conducted on the 28 <sup>th</sup> October 2015 at the request of Kingspan Insulation Ltd, the sponsor of the test.
<b>Provision of test specimens</b>	The specimens were supplied by the sponsor of the test. <b>Exova Warringtonfire</b> was not involved in any selection or sampling procedure.
<b>Conditioning of specimens</b>	<p>The specimens were received on the 13<sup>th</sup> October 2015</p> <p>Prior to test the specimens were stored for 3 days in a standard atmosphere as defined in BS EN 13238:2010 Conditioning Procedures and General Rules for selection of substrates until constant mass was achieved.</p>
<b>Intended application</b>	Thermal insulation.
<b>Substrate</b>	The specimens were tested without a substrate present.
<b>Flame application time</b>	The flame was applied for 30 seconds.

Document No.: 358292

Author: K Hughes

Client: Kingspan Insulation Ltd

Page No.: 4 of 8

Issue Date: 9<sup>th</sup> November 2015

Issue No.: 1



0249



## Description of Test Specimens

The description of the specimens given below has been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

General description		Black foil faced thermoset phenolic insulation board (silver foil on reverse)
Name of manufacturer		Kingspan Insulation Ltd.
Trade name		"Kooltherm K15"
Batch reference		"8100172119-1000"
Date of manufacture		18/09/2015
Overall weight per unit area		See Note 1 below
Thickness		50mm (stated by sponsor) 50mm (determined by Exova Warringtonfire)
Product configuration		<ul style="list-style-type: none"> <li>Black foil facer - perforated</li> <li>Phenolic foam</li> <li>Foil facer - perforated</li> </ul>
Aluminium foil Black in colour (test face)	Product reference	See Note 1 below
	Generic type	Composite foil
	Name of manufacturer	See Note 1 below
	Weight per unit area	See Note 1 below
	Thickness	See Note 1 below
	Colour	"Black Foil"
	Flame retardant details	See Note 2 below
Foam	Product reference	"K15"
	Generic type	Phenolic foam
	Name of manufacturer	Kingspan Insulation Ltd.
	Thickness	50mm
	Density	See Note 1 below
	Colour reference	"Pinkish"
	Flame retardant details	See Note 2 below
Aluminium foil	Product reference	See Note 1 below
	Generic type	Composite foil
	Name of manufacturer	See Note 1 below
	Thickness	See Note 1 below
	Density	See Note 1 below
	Colour reference	"Silver foil"
	Flame retardant details	See Note 2 below
Brief description of manufacturing process		Facings auto adhesively bonded to phenolic core during the manufacturing process.

**Note 1:** The sponsor of the test has provided this information but at the specific request of the sponsor, these details have been omitted from the report and are instead held on the confidential file relating to this investigation.

**Note 2:** The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the component.

Document No.: 358292

Page No.: 5 of 8

Author: K Hughes

Issue Date: 9<sup>th</sup> November 2015

Client: Kingspan Insulation Ltd

Issue No.: 1



0249

## Test Results

### Number of specimens tested

Six specimens were tested, each of which were subjected to surface exposure to flame with the black foil face exposed.

Six specimens were tested, each of which were subjected to edge exposure to flame with the black foil face exposed.

Six specimens were tested, each of which were subjected to edge exposure to flame with the specimen turned at 90° round its vertical axis and the foam face exposed.

### Applicability of test results

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which they were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product which is supplied or used is fully represented by the specimens which were tested.

The test results for the individual specimens, together with observations made during the test and comments on any difficulties encountered during the test are given in Tables 1, 2 and 3.

**On each set of six specimens which were tested, the flame tip did not reach a distance of 150mm before the end of the test.**

### Validity

The specification and interpretation of fire test methods are the subject of ongoing development and refinement. Changes in associated legislation may also occur. For these reasons it is recommended that the relevance of test reports over five years old should be considered by the user. The laboratory that issued the report will be able to offer, on behalf of the legal owner, a review of the procedures adopted for a particular test to ensure that they are consistent with current practices, and if required may endorse the test report.

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of **Exova Warringtonfire**.

Document No.: 358292

Page No.: 6 of 8

Author: K Hughes

Issue Date: 9<sup>th</sup> November 2015

Client: Kingspan Insulation Ltd

Issue No.: 1



0249

**Table 1**
**Test Flame Application Position - Surface of black foil face**

Specimen No.	Ignition Yes/No	Time from start of test for flame tip to reach 150mm (seconds)	Extent of Flame Spread (mm)	Flaming Debris	Glowing	Extent of Damaged Area (mm)	
						Height	Width
1	No	Did not reach	Nil	None	None	35	16
2	No	Did not reach	Nil	None	None	37	19
3	No	Did not reach	Nil	None	None	40	17
4	No	Did not reach	Nil	None	None	41	17
5	No	Did not reach	Nil	None	None	32	15
6	No	Did not reach	Nil	None	None	38	18

**Table 2**
**Test Flame Application Position - Edge of black foil face**

Specimen No.	Ignition Yes/No	Time from start of test for flame tip to reach 150mm (seconds)	Extent of Flame Spread (mm)	Flaming Debris	Glowing	Extent of Damaged Area (mm)	
						Height	Width
1	Yes	Did not reach	30	None	None	48	45
2	Yes	Did not reach	30	None	None	50	47
3	Yes	Did not reach	30	None	None	52	47
4	Yes	Did not reach	30	None	None	52	48
5	Yes	Did not reach	30	None	None	50	48
6	Yes	Did not reach	30	None	None	51	47

**Table 3**
**Test Flame Application Position - Edge of the specimen turned at 90° round its vertical axis and the insulation face exposed**

Specimen No.	Ignition Yes/No	Time from start of test for flame tip to reach 150mm (seconds)	Extent of Flame Spread (mm)	Flaming Debris	Glowing	Extent of Damaged Area (mm)	
						Height	Width
1	No	Did not reach	Nil	None	None	123	19
2	No	Did not reach	Nil	None	None	122	19
3	No	Did not reach	Nil	None	None	125	18
4	No	Did not reach	Nil	None	None	124	17
5	No	Did not reach	Nil	None	None	123	17
6	No	Did not reach	Nil	None	None	120	18

Document No.: 358292

Page No.: 7 of 8

Author: K Hughes

Issue Date: 9<sup>th</sup> November 2015

Client: Kingspan Insulation Ltd

Issue No.: 1



0249

Revision History

Issue No :	Re-issue Date :
Revised By:	Approved By:
Reason for Revision:	

