

## EVERFLEX FIRE MATE SEALANT



Colour	Product Code	Pack Size	Box Qty
White	FIRE	C3	25
Brown	FIREMATEBN	C3	25
Grey	FIREMATEGY	C3	25

### Product Description

EVERFLEX FIRE MATE is a five hour rated, one part, emulsion acrylic based, intumescent Acoustic sealant that gives a firm yet flexible seal to joints in a variety of fire rated structures. Tested following the principles of BS EN 1366-4:2006 as detailed in Warrington Fire Research Report No. 181967 (May 2009). Acoustic rated to BS EN ISO 140/3. Tested for air permeability to EN13141-1. The product, in suitably designed joints will resist the passage of fire for up to 5 hours. The selected fillers used in this formulation also make it suitable for use as an acoustic sealant.

### Benefits

- When exposed to heat, it swells greater than 150% of its original size, creating a char that will resist the passage of fire for up to 5 hours.
- No priming required for most construction substrates
- Permanently flexible with more than 100% elongation to ISO8339
- For use in joints up to 50mm wide.
- Excellent acoustic properties for sound deadening - Average noise reduction of 24db (100-3150Hz)
- Non slump - easy to apply and tool off.
- Fast cure - tack free in 15 minutes.
- Overpaintable.
- Certified under the harmonized European standard EN15651 for façade for interior and exterior applications in compliance with the Construction Product Regulation

### Areas For Use

- Sealing joints, voids and irregular holes in fire walls, partitions and other structures; also for maintaining the integrity of pipes and cables that penetrate them.
- For internal perimeter pointing of fire rated door and window frames.

### Limitations

- Not for use on substrates that may bleed oils, solvents or plasticisers.
- Not for use where joints are constantly immersed in water, or as part of structural glazing systems.

### Surface Preparation

All surfaces must be clean, dry and dust free. All loose or flaking surface coatings, and old sealant and mastic joints, should be removed before application.

### Application

The surfaces to be must be clean, dry and free from dust, grease and other contaminants. Improve adhesion by wiping surface with EVERBUILD GLASS CLEANER allowing all solvent to evaporate before applying sealant. Priming is generally not required, although we always advise testing small areas prior to use. Large voids should first be filled with EVERBUILD FIREFOAM B1 to maximize fire rating.

Cut the tip of the cartridge taking care not to damage the thread. Apply nozzle and cut at an angle of 45° with an opening slightly larger than the gap to be sealed. Apply using a standard sealant gun. Best results will be obtained by keeping an even pressure on the trigger and keeping the gun at a constant angle to the surface being sealed. To ensure a proper bond, always smooth the sealant down with a spatula or piece of wood wetted with linseed oil or white spirits. An improved joint appearance can be achieved by placing masking tape to both sides of the joint, removing within 5 minutes of application

*Single seal joints should be on the fire rated side of the structure.*

### Specific Data

<b>Slump:</b>	Nil in joints up to 50mm and 0mm to ISO7390
<b>Max Joint Width:</b>	50mm
<b>Skin over time:</b>	10 minutes
<b>Tack free time:</b>	15 minutes
<b>Joint movement:</b>	+ - 7.5% of original size
<b>Full Cure:</b>	3 to 5 days, dependent on thickness, ambient temperature and humidity
<b>Fire test temp:</b>	1160°C - intumescent @ ca. 135°C
<b>Cleaning:</b>	Uncured with a dampened cloth
<b>Packaging:</b>	C3 plastic cartridges

### FIRE RATING TABLE

#### FIRE TEST RESULTS – WALL SPECIMENS

SPECEMIN	GAP FACE MATERIAL COMBINATION	WIDTH/DEPTH MM	BACKING MATERIAL	INTEGRITY (MINS)	INSULATION (MINS)
G	Aerated concrete/ Aerated concrete	12/6	PE open cell foam	301*	222
H	Aerated concrete/aerated concrete	30/15	PE open cell foam	301*	301*
I	Aerated concrete/softwood	12/6	PE open cell foam	108	75
J	Aerated concrete/hardwood	12/6	PE open cell foam	153	152
K	Aerated concrete/softwood	30/15	PE open cell foam	114	114
L	Aerated concrete/steel	12/6	PE open cell foam	301*	80

#### FLOOR SPECIMENS

SPECEMIN	GAP FACE MATERIAL COMBINATION	WIDTH/DEPTH MM	BACKING MATERIAL	INTEGRITY (MINS)	INSULATION (MINS)
A	Aerated concrete/aerated concrete	12/6	PE open cell foam	301*	196
B	Aerated concrete/aerated concrete	30/15	PE open cell foam	301*	81
C	Aerated concrete/aerated concrete	50/25	PE open cell foam	301*	74
D	Aerated concrete/steel	12/6	PE open cell foam	288	43
E	Aerated concrete/steel		30/15	301*	41
F	Aerated concrete/steel		50/25	290	35

\*The overall test was discontinued after a period of 301 mins.

#### Health & Safety

Consult MSDS for full list of hazards

#### Storage

Store in cool dry conditions between + 5°C and 30°C. PROTECT FROM FROST

#### Shelf Life

24 months from date of manufacture

*The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.*